



marlon fs®

**Sound Reduction
Index**

Airborne Sound Reduction Index to BS EN ISO140-3: 1995, BS2750: Part 3

Sheet	Sound Reduction Index (dB)	
	MARLON FS	GLASS
3 mm	23	
4 mm	25	29
5 mm	27	30
6 mm	29	31
8 mm	31	32
10 mm	33	33
12 mm	34	34